



## ALFAKOL 6\*

**ALFAKOL 6\* C2TE-S1** - is an Improved, Cementitious adhesive (C2), with reduced Slip (T), extended open time (E), and Deformable (S1), for indoor and outdoor use on floors and walls. Suitable for bonding low and non-absorbent tiles like porcelain tiles, granite, glass mosaic and decorative bricks, regardless of their dimensions, on plastered surfaces, concrete, gypsum and cement boards. Distinguished for its endurance to indoor expansions and contractions associated with underfloor heating systems and to outdoor intense temperature variations, such as balconies and terraces.

### DIRECTIONS FOR USE

**Surface preparation:** The application surface has to be sound, clean, free of loose materials, dust, paint, grease and oils. For better adhesion soak the surface before the application.

**Mixing:** Empty 25kg **ALFAKOL 6\*** into a clean container with 6-7 L cool water and mix with a low rpm, electric mixer until a homogeneous, lump free, mass is obtained. Allow the mixture to mature for 5 minutes and mix again. During use mix periodically, without adding extra water.

**Application:** The tile adhesive should be spread (“combed”) on the substrate using a notched trowel, in order to be uniformly applied on the whole surface. The tiles should be fixed by pressing them in the desired position. The applied mixture must be covered with tiles within 10-20 minutes (depending on temperature, humidity and wind) in order to avoid “skin” formation, i.e. before the adhesive film starts setting.

**Consumption:** 5-6 kg/m<sup>2</sup> depending on the size of the notched trowel, the smoothness of the substrate and the dimensions of the tiles.

**Weather Conditions:** Use at temperatures between +5°C and +35°C. Too high or too low temperatures, it might cause a negative reaction to the product.

**Storage:** Store in factory sealed packages, in dry and shaded places for a minimum of 12 months after production date.

## Technical characteristics (measurement conditions 23°C & 50% R.H.)

Product identity	
Form	Cementitious mortar
Color	White / Grey
Bulk density of dry mortar	1.35±0.1kg/lt.
Dry solid content (%)	100%
Storage	12 months if stored in original, unopened packaging, in dry and shaded places.
Toxicity/ Inflammability	NO
Application data	
Water demand	25kg mortar in 6-7lt. water
pH of fresh mortar	>10
Pot life	4 hours / mix every 1 hour
Application temperature	+5 °C - +35 °C
Grouting	4-6 hours on wall ----- 24 hours on floor
Foot Traffic	24 hours
Consumption	5-6kg/m <sup>2</sup> Depending on use
Final Performances	
Classification according EN12004	C2TE-S1
Temperature resistance	-30°C - +90°C
Open time (30min.)	0.8 N/mm <sup>2</sup>
Initial adhesion strength (28 days)	2.1 N/mm <sup>2</sup>
Adhesion Strength after heat ageing (28 days)	1.9 N/mm <sup>2</sup>
Adhesion strength after water immersion (28 days)	1.5 N/mm <sup>2</sup>
Adhesion strength after freeze-thaw cycles (28 days)	2.0 N/mm <sup>2</sup>
Slip	0.3 mm
Transverse deformation	3.3 mm

**Note:**

The directives that are given above for our products are based on extensive research and experiments that were done by accredited European laboratories. We guarantee the constant and high quality of our products. Also, the information that is provided in this document, constitute the opinion of Producer Company, that however can be effected from others. The users of the product have the responsibility to follow correct processes of hygiene and safety. We do not have any responsibility for any damage or loss by factors that are not controlled by our company. For any other information contact with AVRAAM PITTAKIS and SONSLTD.

# DECLARATION OF PERFORMANCE

in accordance with regulation (EU) No.305/2011, appendix III  
N°: CPR084-CPR - 01/07/2013

1. Unique identification code of the product-type: ALFAKOL 6\* 084
2. Type, batch or serial number or any other element allowing identification of the construction product: The Batch code is printed on package
3. Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer: Improved, deformable, cementitious adhesive with reduced slip and extended open time C2TE-S1, Internal/External wall and floor tiling.
4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required under article 11 (5):

AVRAAM PITTAKIS & SONS LTD  
P.O Box: 33006, 5310 Paralimni, Cyprus,

[www.paralimnitiko.com](http://www.paralimnitiko.com)  
[info@paralimnitiko.com](mailto:info@paralimnitiko.com)

5. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V: **System 3**

6. a. Harmonised Standard: CYS EN 12004:2017

Notified body: A notified testing laboratory, the APPLUS, LGAI TECHNOLOGICAL CENTER, S.A, NB 0370, has performed the determination of the product-type on the basis of Initial Type Testing (ITT) under system 3 and issued the test report N° 08/32301784

7. Declared Performance/s:

C2TE-S1		
Essential characteristics	Performance	Harmonised Technical Specification
Reaction to fire	Class A1	EN 12004:2017
Release of dangerous substances	NPD	
Open time (30 min)	$\geq 0.5 \text{ N/mm}^2$	
Initial Adhesion Strength	$\geq 1 \text{ N/mm}^2$	
Adhesion Strength after Heat Ageing	$\geq 1 \text{ N/mm}^2$	
Adhesion Strength after water immersion	$\geq 1 \text{ N/mm}^2$	
Adhesion Strength after freeze/thaw cycles	$\geq 1 \text{ N/mm}^2$	
Slip	$\leq 0.5 \text{ mm}$	
Transverse deformation	$2.5\text{mm} \leq S1 < 5\text{mm}$	

8. The performance of the product identified above is in conformity with the declared performance/s (point 7). This declaration of performance is issued in accordance with regulation (EU) NO.305/2011 under the sole responsibility of the manufacturer identified above.



, Paralimni, 01/09/2018

Signed for and on behalf of manufacturer by:

Koutsofta Katerina, Chemical Engineer



AVRAAM PITTAKIS & SONS LTD  
P.O. BOX 33006, 5310 PARALIMNI, CYPRUS  
13  
CPR 084 - CPR - 01/07/2013  
ALFAKOL 6\* - 084

**CYS EN 12004: 2017**

**Improved deformable cementitious adhesive with reduced slip and extended open time C2TE-S1**

**Internal/External wall and floor tiling**

**Reaction to fire: Class A1**

**Release of dangerous substances: NPD**

**Open Time (30 min):  $\geq 0.5 \text{ N/mm}^2$**

**Initial Tensile Adhesion Strength  $\geq 1 \text{ N/mm}^2$**

**Tensile Adhesion Strength after Heat Ageing:  $\geq 1 \text{ N/mm}^2$**

**Tensile Adhesion Strength after Water Immersion:  $\geq 1 \text{ N/mm}^2$**

**Tensile Adhesion Strength after Freeze/Thaw Cycles:  $\geq 1 \text{ N/mm}^2$**

**Transverse Deformation:  $2.5\text{mm} \leq S1 < 5\text{mm}$**

**Slip:  $\leq 0.5\text{mm}$**